1		<b>SECTION 32 17 23</b>
2		PAVEMENT MARKINGS
3	PAF	RT 1 - GENERAL
4	1.1	SUMMARY
5		A.Section Includes:
6		1. Pavement Markings
7		a. Thermoplastic, hot-applied, spray (HAS) pavement markings
8		b. Thermoplastic, hot-applied, extruded (HAE) pavement markings
9		c. Preformed polymer tape
10		d. Preformed heat-activated thermoplastic tape
11		e. Preformed Contrast Markings
12		2. Raised markers
13		3. Work zone markings
14		4. Removal of pavement markings and markers
15		B. Deviations from this City of Fort Worth Standard Specification
16		1. None.
17		C.Related Specification Sections include, but are not necessarily limited to:
18		1. Division 0 – Bidding Requirements, Contract Forms and Conditions of the Contract
19		2. Division 1 – General Requirements
20	1.2	PRICE AND PAYMENT PROCEDURES
21		A.Measurement and Payment
22		1. Pavement Markings
23		a. Measurement
24		1) Measurement for this Item shall be per linear foot of material placed.
25		b. Payment
26		1) The work performed and materials furnished in accordance with this Item
27 28		and measured as provided under "Measurement" shall be paid for at the unit price bid per linear foot of "Pvmt Marking" installed for:
29		a) Various Widths
30		b) Various Types
31		c) Various Materials
32		d) Various Colors
33		c. The price bid shall include:
34 35		<ol> <li>Installation of Pavement Marking</li> <li>Glass beads, when required</li> </ol>
35 36		3) Surface preparation
37		4) Clean-up
38		5) Testing (when required)
39		2. Legends
40		a. Measurement
41		1) Measurement for this Item shall be per each Legend installed.

1		b. Payment
2		1) The work performed and materials furnished in accordance with this Item
3		shall be paid for at the unit price bid per each "Legend" installed for:
4		a) Various types
5		b) Various applications
6		c. The price bid shall include:
7		1) Installation of Pavement Marking
8		2) Glass beads, when required
9		3) Surface preparation
10		4) Clean-up
11		5) Testing
12	3.	Preformed Thermoplastic – Contrast Markings
13	3.	a. Measurement
14		1) Measurement for this Item shall be per linear foot of material placed or per
15		each for legend items
16		<ul><li>b. Payment</li><li>1) The work performed and materials furnished in accordance with this Item</li></ul>
17		*
18		shall be paid for at the unit price bid per linear foot or per each for legends for "Preformed Thermoplastic – Contract Markings" installed for:
19		a) Various Widths
20		
21		b) Various Types
22		c) Various Applications
23 24		<ul><li>c. The price bid shall include:</li><li>1) Installation of Contrast Markings, including solid black and solid white or</li></ul>
25		yellow material as preformed
26		2) Railroad Legend shall include X and RR legend markings and three 24"
27		stop bars
28		a) â a
29		<ul><li>3) Surface preparation</li><li>4) Clean-up</li></ul>
30		5) Testing
	4	,
31	4.	Raised Markers
32		a. Measurement
33		1) Measurement for this Item shall be per each Raised Marker installed.
34		b. Payment
35		1) The work performed and materials furnished in accordance with this Item
36		shall be paid for at the unit price bid per each "Raised Marker" installed for:
37		a) Various types
38		c. The price bid shall include:
39		1) Installation of Raised Markers
40		2) Surface preparation
41		3) Clean-up
42		4) Testing
43	5.	Work Zone Tab Markers
44		a. Measurement
45		1) Measurement for this Item shall be per each Tab Marker installed.
46		b. Payment
47		1) The work performed and materials furnished in accordance with this Item
48		shall be paid for at the unit price bid per each "Tab Marker" installed for:
49		a) Various types

1 2		<ul><li>c. The price bid shall include:</li><li>1) Installation of Tab Work Zone Markers</li></ul>
	(	
3	0.	Fire Lane Markings
4 5		a. Measurement  1) Measurement for this Item shall be per the linear foot
6		<ul><li>1) Measurement for this Item shall be per the linear foot.</li><li>b. Payment</li></ul>
7		1) The work performed and materials furnished in accordance with this Item
8		and measured as provided under "Measurement" shall be paid for at the unit
9		price bid per linear foot of "Fire Lane Marking" installed.
10		c. The price bid shall include:
11		1) Surface preparation
12		2) Clean-up
13		3) Testing
14	7.	Pavement Marking Removal
15	, ,	a. Measurement
16		1) Measure for this Item shall be per linear foot.
17		b. Payment
18		1) The work performed and materials furnished in accordance with this Item
19		and measured as provided under "Measurement" shall be paid for at the unit
20		price bid per linear foot of "Remove Pvmt Marking" performed for:
21		a) Various widths
22		c. The price bid shall include:
23		1) Removal of Pavement Markings
24		2) Clean-up
25	8.	Raised Marker Removal
26		a. Measurement
27		1) Measurement for this Item shall be per each Pavement Marker removed.
28		b. Payment
29		1) The work performed and materials furnished in accordance with this Item
30		shall be paid for at the unit price bid per each "Remove Raised Marker"
31		performed.
32		c. The price bid shall include:
33		1) Removal of each Marker
34		2) Disposal of removed materials
35		3) Clean-up
36	9.	$\epsilon$
37		a. Measurement
38		1) Measure for this Item shall be per each Legend removed.
39		b. Payment
40		1) The work performed and materials furnished in accordance with this Item
41		and measured as provided under "Measurement" shall be paid for at the unit
42 43		price bid per linear foot of "Remove Legend" performed for:
43 44		<ul><li>a) Various types</li><li>b) Various applications</li></ul>
44 45		c. The price bid shall include:
46		1) Removal of Pavement Markings
47		2) Clean-up
• •		-) wp

1	1.3	REFERENCES		
2		A.Reference Standards		
3 4 5		1. Reference standards cited in this Specification refer to the current reference standard published at the time of the latest revision date logged at the end of this Specification, unless a date is specifically cited.		
6 7		Texas Manual on Uniform Traffic Control Devices (MUTCD), 2011 Edition     a. Part 3, Markings		
8 9		<ol> <li>American Association of State Highway and Transportation Officials (AASHTO)</li> <li>a. Standard Specification for Glass Beads Used in Pavement Markings, M 247-09</li> </ol>		
10 11		<ul><li>4. Federal Highway Administration (FHWA)</li><li>a. 23 CFR Part 655, FHWA Docket No. FHWA-2009-0139</li></ul>		
12 13 14 15 16 17		<ul> <li>5. Texas Department of Transportation (TxDOT)</li> <li>a. DMS-4200, Pavement Markers (Reflectorized)</li> <li>b. DMS-4300, Traffic Buttons</li> <li>c. DMS-8220, Hot Applied Thermoplastic</li> <li>d. DMS-8240, Permanent Prefabricated Pavement Markings</li> <li>e. DMS-8241, Removable Prefabricated Pavement Markings</li> </ul>		
18		f. DMS-8242, Temporary Flexible-Reflective Road Marker Tabs		
19	1.4	ADMINISTRATIVE REQUIREMENTS [NOT USED]		
20	1.5	SUBMITTALS		
21		A.Submittals shall be in accordance with Section 01 33 00.		
22 23		B. All submittals shall be approved by the City prior to delivery and/or fabrication for specials.		
24	1.6	ACTION SUBMITTALS/INFORMATIONAL SUBMITTALS [NOT USED]		
25	1.7	CLOSEOUT SUBMITTALS [NOT USED]		
26	1.8	MAINTENANCE MATERIAL SUBMITTALS [NOT USED]		
27	1.9	QUALITY ASSURANCE [NOT USED]		
28	1.10	DELIVERY, STORAGE, AND HANDLING		
29 30 31		<ul> <li>A.Storage and Handling Requirements</li> <li>1. The Contractor shall secure and maintain a location to store the material in accordance with Section 01 50 00.</li> </ul>		
32	1.11	FIELD [SITE] CONDITIONS [NOT USED]		
33	1.12	WARRANTY [NOT USED]		

# 34 PART 2 - PRODUCTS

# 35 2.1 OWNER-SUPPLIED PRODUCTS

- 36 A.New Products
- 1. Refer to Drawings to determine if there are owner-supplied products for the Project.

# 2.2 MATERIALS

2	A.Manufacturers
3	1. Only the manufacturers as listed in the City's Standard Products List will be
4	considered as shown in Section 01 60 00.
5	a. The manufacturer must comply with this Specification and related Sections.
6 7	2. Any product that is not listed on the Standard Products List is considered a substitution and shall be submitted in accordance with Section 01 25 00.
8	B. Materials
9	1. Pavement Markings
10	a. Thermoplastic, hot applied, spray
11	Refer to Drawings and City Standard Detail Drawings for width of
12	longitudinal lines.
13	2) Product shall be especially compounded for traffic markings.
14	3) When placed on the roadway, the markings shall not be slippery when wet,
15	lift from pavement under normal weather conditions nor exhibit a tacky
16	exposed surface.
17	4) Cold ductility of the material shall permit normal road surface expansion
18	and contraction without chipping or cracking.
19	5) The markings shall retain their original color, dimensions and placement
20	under normal traffic conditions at road surface temperatures of 158 degrees
21	Fahrenheit and below.
22	6) Markings shall have uniform cross-section, clean edges, square ends and no
23	evidence of tracking.
24	7) The density and quality of the material shall be uniform throughout the
25	markings.
26	8) The thickness shall be uniform throughout the length and width of the
27	markings.  O) The markings shall be 05 percent free of heles and voids, and free of
28 29	9) The markings shall be 95 percent free of holes and voids, and free of blisters for a minimum of 60 days after application.
30	10) The material shall not deteriorate by contact with sodium chloride, calcium
31	chloride or other chemicals used to prevent roadway ice or because of the oil
32	content of pavement markings or from oil droppings or other effects of traffic.
33	11) The material shall not prohibit adhesion of other thermoplastic markings if,
34	at some future time, new markings are placed over existing material.
35	a) New material shall bond itself to the old line in such a manner that no
36	splitting or separation takes place.
37	12) The markings placed on the roadway shall be completely retroreflective
38	both internally and externally with traffic beads and shall exhibit uniform
39	retro-directive reflectance.
40	13) Traffic beads
41	a) Manufactured from glass
42	b) Spherical in shape
43	c) Essentially free of sharp angular particles
44	d) Essentially free of particles showing cloudiness, surface scoring or
45	surface scratching
46	e) Water white in color
47	f) Applied at a uniform rate

1	g) Meet or exceed Specifications shown in AASHTO Standard
2	Specification for Glass Beads Used in Pavement Markings, AASHTO
3	Designation: M 247-09.
4	b. Thermoplastic, hot applied, extruded
5	1) Product shall be especially compounded for traffic markings
6	2) When placed on the roadway, the markings shall not be slippery when wet,
7	lift from pavement under normal weather conditions nor exhibit a tacky
8	exposed surface.
9	3) Cold ductility of the material shall permit normal road surface expansion
10	and contraction without chipping or cracking.
11	4) The markings shall retain their original color, dimensions and placement
12	under normal traffic conditions at road surface temperatures of 158 degrees
13	Fahrenheit and below.
14	5) Markings shall have uniform cross-section, clean edges, square ends and no
15	evidence of tracking.
16	6) The density and quality of the material shall be uniform throughout the
17	markings.
18	7) The thickness shall be uniform throughout the length and width of the
19	markings.
20	8) The markings shall be 95 percent free of holes and voids, and free of
21	blisters for a minimum of 60 days after application.
22	9) The minimum thickness of the marking, as measured above the plane
23	formed by the pavement surface, shall not be less than 1/8 inch in the center
24	of the marking and $3/32$ inch at a distance of $\frac{1}{2}$ inch from the edge.
25	10) Maximum thickness shall be 3/16 inch.
26	11) The material shall not deteriorate by contact with sodium chloride, calcium
27	chloride or other chemicals used to prevent roadway ice or because of the oil
28	content of pavement markings or from oil droppings or other effects of traffic
29	12) The material shall not prohibit adhesion of other thermoplastic markings if,
30	at some future time, new markings are placed over existing material. New
31	material shall bond itself to the old line in such a manner that no splitting or
32	separation takes place.
33	13) The markings placed on the roadway shall be completely retroreflective
34	both internally and externally with traffic beads and shall exhibit uniform
35	retro-directive reflectance.
36	14) Traffic beads
37	a) Manufactured from glass
38	b) Spherical in shape
39	c) Essentially free of sharp angular particles
40	d) Essentially free of particles showing cloudiness, surface scoring or
41	surface scratching
42	e) Water white in color
43	f) Applied at a uniform rate
44	g) Meet or exceed Specifications shown in AASHTO Standard
45	Specification for Glass Beads Used in Pavement Markings, AASHTO
46	Designation: M 247-09.
47	c. Preformed Polymer Tape
48	1) Material shall meet or exceed the Specifications for SWARCO Director 35
49	3M High Performance Tape Series 3801 ES, or approved equal.
50	d. Preformed Heat-Activated Thermoplastic Tape

- the following types:

  1) Type I-C, white body, 1 face reflects white
  - 2) Type II-A-A, yellow body, 2 faces reflect amber
  - 3) Type II-C-R, white body, 1 face reflects white, the other red

## 3. Work Zone Markings

- a. Tabs
  - 1) Temporary flexible-reflective roadway marker tabs shall meet requirements of TxDOT DMS-8242, "Temporary Flexible-Reflective Road Marker Tabs."
  - 2) Removable markings shall not be used to simulate edge lines.
  - 3) No segment of roadway open to traffic shall remain without permanent pavement markings for a period greater than 14 calendar days.
- b. Raised Markers
  - 1) All raised pavement markers shall meet the requirements of DMS-4200.
- c. Striping
  - 1) Work Zone striping shall meet or exceed the TxDOT Specification DMS-8200.

### 2.3 ACCESSORIES [NOT USED]

#### 2.4 SOURCE QUALITY CONTROL

#### 30 A.Performance

13

141516

17 18

19

20 21

22

23 24

25

26

2728

29

31

32

34

35

36

37

38

39

1. Minimum maintained retroreflectivity levels for longitudinal markings shall meet the requirements detailed in the table below for a minimum of 30 calendar days.

	Posted Speed (mph)		
	≤ 30	35 – 50	≥ 55
2-lane roads with centerline markings only (1)	n/a	100	250
All other roads (2)	n/a	50	100

- (1) Measured at standard 30-m geometry in units of mcd/m<sup>2</sup>/lux.
- (2) Exceptions:

A. When raised reflective pavement markings (RRPMs) supplement or substitute for a longitudinal line, minimum pavement marking retroreflectivity levels are not applicable as long as the RRPMs are maintained so that at least 3 are visible from any position along that line during nighttime conditions.

B. When continuous roadway lighting assures that the markings are visible, minimum pavement marking retroreflectivity levels are not applicable.

### 1 PART 3 - EXECUTION

### 3.1 EXAMINATION [NOT USED]

#### 3.2 PREPARATION

2

3

5

6 7

8

9

10

11

12 13

14

16

17 18

19

2021

22

23 24

25

26

27

28 29

30

31

3233

34

35

36

3738

39 40

41

42

#### 4 A.Pavement Conditions

- 1. Roadway surfaces shall be free of dirt, grease, loose and/or flaking existing markings and other forms of contamination.
- 2. New Portland cement concrete surfaces shall be cleaned sufficiently to remove the curing membrane.
- 3. Pavement to which material is to be applied shall be completely dry.
- 4. Pavement shall be considered dry, if, on a sunny day after observation for 15 minutes, no condensation develops on the underside of a 1 square foot piece of clear plastic that has been placed on the pavement and weighted on the edges.
- 5. Equipment and methods used for surface preparation shall not damage the pavement or present a hazard to motorists or pedestrians.

#### 15 3.3 INSTALLATION

#### A.General

- 1. The materials shall be applied according to the manufacturer's recommendations.
- 2. Markings and markers shall be applied within temperature limits recommended by the material manufacturer, and shall be applied on clean, dry pavement having a surface temperature above 50 degrees Fahrenheit.
- 3. Markings that are not properly applied due to faulty application methods or being placed in the wrong position or alignment shall be removed and replaced by the Contractor at the Contractor's expense. If the mistake is such that it would be confusing or hazardous to motorists, it shall be remedied the same day of notification. Notification will be made by phone and confirmed by fax. Other mistakes shall be remedied within 5 days of written notification.
- 4. When markings are applied on roadways open to traffic, care will be taken to ensure that proper safety precautions are followed, including the use of signs, cones, barricades, flaggers, etc.
- 5. Freshly applied markings shall be protected from traffic damage and disfigurement.
- 6. Temperature of the material must be equal to the temperature of the road surface before allowing traffic to travel on it.

## **B.** Pavement Markings

- 1. Thermoplastic, hot applied, spray
  - a. This method shall be used to install and replace long lines centerlines, lane lines, edge lines, turn lanes, and dots.
  - b. Markings shall be applied at a 110-mil thickness.
  - c. Markings shall be applied at a 90-mil thickness when placed over existing markings.
  - d. A sealer shall be used if concrete or asphalt is older than three (3) years.
- e. Typical setting time shall be between 4 minutes and 10 minutes depending upon the roadway surface temperature and the humidity factor.

2 3 4		lines, and turn lanes. Refer to City Standard Detail Drawings for placement. g. Minimum retroreflectivity of markings shall meet or exceed values shown in subparagraph 2.4.A.1 of this Specification.
5	2.	Thermoplastic, hot applied, extruded
6		a. This method shall be used to install and replace crosswalks and stop-lines.
7		b. Markings shall be applied at a 125-mil thickness.
8		c. Minimum retroreflectivity of markings shall meet or exceed values shown in
9		this Specification.
10	3.	Preformed Polymer Tape
11		a. This method shall be used to install and replace crosswalks, stop-lines, and
12		legends.
13		b. The applied marking shall adhere to the pavement surface with no slippage or
14		lifting and have square ends, straight lines and clean edges.
15		c. Minimum retroreflectivity of markings shall meet or exceed values shown in
16	4	this Specification.
17	4.	Preformed Heat-Activated Thermoplastic Tape
18		a. This method shall be used to install and replace crosswalks, stop-lines, and
19 20		legends. b. The applied marking shall adhere to the pavement surface with no slippage or
21		lifting and have square ends, straight lines and clean edges.
22		c. Minimum retroreflectivity of markings shall meet or exceed values shown in
23		this Specification.
24	C.Rais	ed Markers
25	1.	All permanent raised pavement markers on Portland Cement roadways shall be
26	1.	installed with epoxy adhesive. Bituminous adhesive is not acceptable.
27 28	2.	All permanent raised pavement markers on new asphalt roadways may be installed with epoxy or bituminous adhesive.
29	3.	A chalk line, chain or equivalent shall be used during layout to ensure that
30	5.	individual markers are properly aligned. All markers shall be placed uniformly
31		along the line to achieve a smooth continuous appearance.
32	D.Wor	k Zone Markings
33	1.	Work shall be performed with as little disruption to traffic as possible.
34		Install longitudinal markings on pavement surfaces before opening to traffic.
	_	
35 36	3.	Maintain lane alignment traffic control devices and operations until markings are installed.
37	4.	Install markings in proper alignment in accordance with the Texas MUTCD and as
38		shown on the Drawings.
39	5.	Place standard longitudinal lines no sooner than 3 calendar days after the placement

of a surface treatment, unless otherwise shown on the Drawings.

6. Place markings in proper alignment with the location of the final pavement

7. Do not use raised pavement markers for words, symbols, shapes, or diagonal or

f. Retroreflective raised markers shall be used to supplement the centerlines, lane

markings.

transverse lines.

1

40

41 42

43

1 8. All markings shall be visible from a distance of 300 feet in daylight conditions and 2 from a distance of at least 160 feet in nighttime conditions, illuminated by lowbeam automobile headlight. 3 4 9. The daytime and nighttime reflected color of the markings must be distinctly white or yellow. 5 10. The markings must exhibit uniform retroreflective characteristics. 6 7 11. Epoxy adhesives shall not be used to work zone markings. REMOVALS 8 3.4 9 1. Pavement Marking and Marker Removal 10 a. The industry's best practice shall be used to remove existing pavement markings and markers. 11 b. If the roadway is being damaged during the marker removal, Work shall be 12 halted until consultation with the City. 13 c. Removals shall be done in such a matter that color and texture contrast of the 14 payement surface will be held to a minimum. 15 d. Repair damage to asphaltic surfaces, such as spalling, shelling, etc., greater than 16 ½ inch in depth resulting from the removal of pavement markings and markers. 17 18 Driveway patch asphalt emulsion may be broom applied to reseal damage to 19 asphaltic surfaces. e. Dispose of markers in accordance with federal, state, and local regulations. 20 21 f. Use any of the following methods unless otherwise shown on the Drawings. 1) Surface Treatment Method 22 a) Apply surface treatment at rates shown on the Drawings or as directed. 23 Place a surface treatment a minimum of 2 feet wide to cover the existing 24 25 marking. 26 b) Place a surface treatment, thin overlay, or microsurfacing a minimum of 1 lane in width in areas where directional changes of traffic are 27 involved or in other areas as directed by the City. 28 29 2) Burn Method a) Use an approved burning method. 30 b) For thermoplastic pavement markings or prefabricated pavement 31 32 markings, heat may be applied to remove the bulk of the marking material 33 prior to blast cleaning. 34 c) When using heat, avoid spalling pavement surfaces. d) Sweeping or light blast cleaning may be used to remove minor residue. 35 3) Blasting Method 36 37 a) Use a blasting method such as water blasting, abrasive blasting, water 38 abrasive blasting, shot blasting, slurry blasting, water-injected abrasive blasting, or brush blasting as approved. 39 b) Remove pavement markings on concrete surfaces by a blasting method 40 only. 41 4) Mechanical Method 42 a) Use any mechanical method except grinding. 43 b) Flail milling is acceptable in the removal of markings on asphalt and 44

marking or marker removal.

concrete surfaces.

2. If a location is to be paved over, no additional compensation will be allowed for

45

- 1 3.5 REPAIR / RESTORATION [NOT USED]
- 2 3.6 RE-INSTALLATION [NOT USED]
- 3 3.7 FIELD QUALITY CONTROL
- 4 A.All lines must have clean edges, square ends, and be uniform cross-section.
- 5 B. The density and quality of markings shall be uniform throughout their thickness.
- 6 C. The applied markings shall have no more than 5 percent, by area, of holes or voids and shall be free of blisters.
- 8 3.8 SYSTEM STARTUP [NOT USED]
- 9 **3.9 ADJUSTING [NOT USED]**
- **3.10 CLEANING**
- 11 A.Contractor shall clean up and remove all loose material resulting from construction operations.
- 13 3.11 CLOSEOUT ACTIVITIES [NOT USED]
- 14 3.12 PROTECTION [NOT USED]
- 15 3.13 MAINTENANCE [NOT USED]
- 16 3.14 ATTACHMENTS [NOT USED]

### 17 END OF SECTION

Revision Log

DATE NAME SUMMARY OF CHANGE

11/22/13 S. Arnold Removed paint type marking, updated references, added sealer language

6/10/22 M Owen 1.1 A and 1.2 A – Revised to address preformed "contrast" pavement markings